


## TEM Standards for Resolution & Magnification

### Perforated Carbon Films

A carbon film containing many small holes of various sizes mounted on a 400 mesh 3mm  $\varnothing$  grid, used for correcting astigmatism and for checking the performance of the electron microscope. It is one of the quickest and easiest ways to check microscope resolution. The holes are circular with smooth edges.

**C061** Perforated carbon film each



C061

### Lattice Plane Specimens


Crystal lattice plane specimens provide two measurement checks. They give a good test of microscope stability and as the spacing of the lattice is accurately known from X-ray measurements, they provide a calibration of magnification in the upper range of microscope magnification.

### Copper Phthalocyanine

Plane spacing 1.0nm

Well documented in the literature for TEM the spacing gives a convenient test but the specimens are beam sensitive and quickly lose their crystallinity under the electron beam.

**P138** Copper phthalocyanine on 3mm grid each




P138

### Chloro-Copper Phthalocyanine

Plane spacing 1.75 and 1.3nm

More irradiation resistant than copper phthalocyanine and therefore better for the visualisation of lattice planes. The sample must be tilted at  $26.5^\circ$  to the horizontal to reveal the spacings. Owing to preparation difficulties with this specimen the grid coverage is fragmentary and normal grid coverage is *not* achieved.

**P402** Chloro-copper phthalocyanine crystals on 3mm grid each




P402

### Crocidolite

Plane spacing 0.9nm and 0.45nm

The 0.9 spacing (020) is oriented along the axis of the crocidolite fibres. The 0.45 spacing appears at an angle of about  $60^\circ$  to this in suitable crystal orientations


**P222** Crocidolite on 3mm grid each




### Potassium Chloroplatinate

Plane spacing 0.56nm

**P067** Potassium chloroplatinate crystal on 3mm grid each



P067




P068

## Graphitised Carbon Black

Plane spacing 0.34nm

Graphitised carbon black is stable and highly reproducible and is a popular standard resolution test for TEM's.

**P068** Graphitised carbon black on 3mm grid. each




P066

## Single Crystal Gold Foil

Plane spacing 0.204nm, 0.143nm and 0.102nm

Higher resolution TEM's can be checked for resolution, image quality, magnification and instrumental stability by setting up the conditions for imaging 0.204nm, 0.143nm and 0.102nm planar spacings in these specially prepared crystals. The tests are particularly recommended if height adjustments are made on the specimen stage.

**P066** Oriented single crystal gold foil on 3mm gold grid each



C260

## High Resolution TEM Test Specimens

### Gold Particles on Carbon Film


Finely dispersed thin gold particles for tests of high resolution imaging capabilities of TEM's giving some advantages over Single Crystal Gold. The checking of image quality, magnification and instrumental stability can all be readily undertaken, but for the determination of resolution this gold particle specimen is superior since it offers a choice of crystalline orientations on static or low tilt stages. In addition the thickness of the crystalline material is easily calculated from the projected shape of the gold crystal.

**C260** High resolution test specimen gold on carbon 3mm grid each

## Evaporated Platinum/Iridium

Evaporated platinum/iridium on a perforated carbon film. The support film provides holes for ease of focus and astigmatism correction. The grains of evaporated metal provide dense particles for resolution checks by the particle separation test

**C167** Platinum/Iridium on perforated carbon on 3mm grid each




C167

## Shadowed Polystyrene Latex Particles

Shadowed latex particles of  $0.22\mu\text{m}$   $\varnothing$  provide dense markers and at the edges of the metal shadowing small metal aggregates may be found for particle separation resolution checks.

**P105** Polystyrene latex particles shadowed with palladium/platinum alloy on 3mm grid

Other sizes available:  
 $0.091\mu\text{m}$   $0.142\mu\text{m}$   $0.173\mu\text{m}$   $0.330\mu\text{m}$   $0.497\mu\text{m}$   $1.090\mu\text{m}$




P105

## Gold Shadowed Latex

Heavily gold shadowed latex particles  $0.22\mu\text{m}$   $\varnothing$  on a carbon film. The gold forms islands of strongly scattering material and produces a test object suitable for **STEM**.

**C168** Gold shadowed polystyrene latex particles on 3mm grid each




C168

## Ferritin

Some ferritin molecules display a quad structure with a separation of  $1.25\text{nm}$ . This is useful as a resolution check. The ferritin is dispersed on a formvar/carbon substrate.

**F072** Ferritin on 3mm grid each




F072

## Combined Test Specimen

A perforated carbon film is shadowed with gold onto which graphitised carbon particles are deposited. These particles viewed over the holes may be used to assess factors limiting microscope performance. The evaporated gold forms small polycrystalline islands and within these islands, lattice fringes can be resolved.

This specimen can also be used for the **measurement of contamination rates in the electron microscope** by noting the deposition rate of carbon within the holes found in the gold film.

**S529** Combined test specimen on 3mm grid each




S529

## HVEM Standard

Low contrast on the viewing screen makes normal test specimens difficult to see in the HVEM. These specimens are grids coated with a thick layer of evaporated gold which forms crystallites containing lines of strong diffraction contrast. These are of different spacings allowing the performance to be checked at various levels.

**S530** HVEM test specimen, evaporated gold on 3mm grid each



S530